

LEMON PETROLEUM JELLY

TEST	TEST METHOD	VALUE
Color (Lovibond) cell 1"	IP - 17	2 ≥
Sp-Gravity at 25 °C	ASTM-D - 1298	0.79 – 0.84
Viscosity at 100 °C	ASTM-D - 445	4.5 - 5
Congeaing Point °C	ASTM-D - 938	48 - 52
Drop Melting Point°C	ASTM-D - 127	54- 58
Penetration 0.1mm at 25 °C	ASTM-D - 937	110 - 150
Flash Point°C	ASTM-D - 92	Min 200
Acidity or Alkalinity	BP-2020	Passed

APPLICATIONS

1. Electrical insulator
2. Wood industry
3. Fluid agent for molding and apply in leather industries
4. Anti-wear and anti-fatigue for machinery
5. Anticorrosion for metals
6. Cosmetic and Skin Care
7. Lubricant for plastic and metal objects

PACKING

1. Plastic drums with: capacities of 175 kg and 50 kg
2. Steel drums with: capacities of 175 kg and 50kg