

SUPER SNOW WHITE PETROLEUM JELLY

TEST	TEST METHOD	VALUE
Color (Lovibond) cell 1"	IP - 17	0.1 – 0.3
Sp-Gravity at 25 °C	ASTM-D - 1298	0.79 – 0.84
Viscosity at 100 °C	ASTM-D - 445	4.5 - 6
Congearing Point °C	ASTM-D - 938	52 - 56
Drop Melting Point°C	ASTM-D - 127	56- 62
Penetration 0.1mm at 25 °C	ASTM-D - 937	110 - 140
Flash Point°C	ASTM-D - 92	Min 200
Acidity or Alkalinity	BP-2020	Passed

APPLICATIONS

1. Cosmetic and Skin Care
2. Lubricant for plastic and metal objects
3. Anticorrosion for metals
4. Anti-wear and anti-fatigue for machinery
5. Fluid agent for molding and apply in leather industries
6. Electrical insulator
7. Wood industry

PACKING

1. Plastic drums with: capacities of 175 kg and 50 kg
2. Steel drums with: capacities of 175 kg and 50kg