



Knifing Paste Filler

PRODUCT DESCRIPTION

Indigo Knifing Paste Filler is a solvent based filler for wood and metal surfaces. It can be applied using a putty knife and is made available at ready to use consistency in white & grey colours, with white designed for use on wood and grey for use on metal.



PERFORMANCE FEATURES & BENEFITS

1. Easy to apply
2. Good filling & leveling

FINISH

MATT

GLOSS

WASHABILITY

NO

LOW

MEDIUM

HIGH

RECOMMENDED USES

AREA



INTERIOR



EXTERIOR

SURFACES

Wood (KPF White), Metal (KPF Grey)

APPLICATION DETAILS & SURFACE PREPARATION

MIXING



Mix well before use

TOOLS



Putty blade

THINNING



Turpentine

THINNING RATIO



5% by volume, if required

SURFACE DRYING TIME



Surface Dry in 30 Min.

FILLING



NA

APPLICATION ENVIRONMENT



Temperature: 10-40 Degree
Humidity: Below 80%

CLEANING



Clean the surface of loose paint, dust and grease. Wipe clean using turpentine and allow to dry.

SURFACE PREPARATION



Sand the surface with abrasive paper 180 and wipe clean. Metal or wooded surface must be primed using appropriate primer or undercoat prior to application of Knifing Paste Filler.

APPLICATION



For best results apply using a putty blade. In case the dent is large, ensure that Indigo Knifing Paste Filler is applied in thin coats, with recommended drying time between coats, instead of filling the dent in one thick coat. Intercoat sanding is recommended using abrasive paper grit no.220 and over coat with primer before applying topcoat.

SAFETY FEATURES



Non- flammable
No added Lead, Mercury or Chromium compounds

Spray application: Air-assisted spray application at pressure 25 - 30 psi

* Recoat period is quoted for 25° C and 50% Relative Humidity; these may vary under different conditions.

TECHNICAL DATA

Coverage	1 Coat: 15 - 20 sqft/Kg**
Drying Time	4-6 hours
Sheen level	NA
Flash point	35°C
Stability of thinned paint	NA
Appearance	Semi Solid / thick paste
Solids	85+/-3
Specific gravity	NA
Recommended DFT	NA
Viscosity	300 -350 by Penetrometer
Pot life	NA
Shelf life	24 Months
Contrast ratio	NA

**Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application as well as surface roughness.

PRECAUTIONS

1. Build up in thin layers and not in one thick layer.
2. Apply appropriate primer before and after application of Knifing paste filler.

POST APPLICATION INSTRUCTIONS

Always overcoat with Indigo PU Super Gloss Enamel or other topcoat within 48 hrs

AVAILABLE PACK SIZE

Available in:



0.5 Kg



1 Kg



2 Kg



5 Kg



20 Kg

SHADE RANGE

White & Grey



INDIGO

Be surprised!