

Sleek HS Melamine Topcoat

PRODUCT DESCRIPTION

Indigo Sleek HS Melamine system comprising of Sealer & Topcoat is a quick drying two pack system designed for the protection and beautification of interior furniture & joinery.



PERFORMANCE FEATURES & BENEFITS

- Quick drying
- High-solid formulation for better filling of wood grains
- Extra durable



MIXING RATIO

9:1 by volume (9 parts of base :1 part of hardener)

RECOMMENDED USES

AREA



EXTERIOR

SURFACES

It can be used on all types of interior wood like doors, windows, furniture, kitchen cabinets etc.

APPLICATION DETAILS & SURFACE PREPARATION



Shake well before use

TOOLS



Brush, Spray

THINNING



* For Brush application: Sleek Melamine For Spray application: Sleek Melamine **Spraying Thinner**

THINNING RATIO

Sleek Melamine Thinner -Brushing -20 -30 % Sleek Melamine Thinner -Spraying -30-40 %

SURFACE DRYING TIME



10-15 minutes at 30°C

FILLING



Sleek HS Melamine Sealer

APPLICATION ENVIRONMENT



10-40 Degree Humidity: Below 80%

CIFANING



Ensure that the wood is seasoned and the surface is well-dried.

• To remove the oiliness inherent to tanin rich wood such as teak and rose wood, wipe dean with NC thinner.

SURFACE PREPARATION



· Sand the wooden substrate along the grains, sequentially, with abrasive paper from grit numbers 80 to 180. • The dust, dirt that comes out during the sanding process should be totally removed. • Apply 2-3 coats of Sleek HS Melamine Sealer depending on the filling required. Drying time between coats 3-4 hours & inter-coat sanding using abrasive paper grit number 320.

APPLICATION



Apply 2 coats of Sleek HS Melamine Topcoat by brush / spray with 4-6 hours drying time between coats. Intercoat sanding using abrasive paper grit number 400

SAFETY FEATURES



No added Lead, Mercury or Chromium compounds

TECHNICAL DATA	
Coverage	60-70 Sq.feet/Liter/Coat
Drying Time	4-5 hours
Sheen level	90-95° - Glossy
	10-15° - Matt
Flash point	Above 23°C.
Stability of thinned paint	8 to 10 hours pot life
Appearance	Clear
Solids	62+/-1%
Specific gravity	1
Recommended DFT	30 to 35 microns per coat
Viscosity @25°C by Stormer Viscometer -	
Pot life	8-10 hours after base &
	hardener are mixed at 30°C
Shelf life	12 months
Contrast ratio	NA

*Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application as well as surface roughness.

PRECAUTIONS

- Flammable
- Keep away from heat, sparks etc.
- Use appropriate protection during application.
- Ensure adequate ventillation during application.

POST APPLICATION INSTRUCTIONS

_

Available in: 500 ml 1 Ltr 4 Ltr 10 Ltr 20 Ltr

SHADE RANGE

NA



For more information on our products and services contact 0994 666 3368 or visit us at www.indigopaints.com INDIGO Paints Pvt Ltd, 103 Montreal, Baner Road 411 045, India