

Time	Kiln Feed CaCO ₃	Clinker Lt / Weight	Av. Clinker Analysis
9.00	Stop	Stop	S ₂ O ₃ 21.66
10.00	--	--	Al ₂ O ₃ 4.47
11.00	--	--	Fe ₂ O ₃ 3.48
12.00	--	--	CuO 64.22
1.00	--	--	MgO 3.60
2.00	77.93	1250	So ₃ 0.70
3.00	78.43	1350	LSF 0.92
4.00	78.43	1250	SM 2.72
5.00	77.43	1300	AM 1.28
6.00	77.68	1300	C ₂ S 55.58
7.00	77.93	1250	C ₂ S 20.26
8.00	77.43	*1200	C ₃ A 5.96
9.00	77.19	*1200	C ₄ AF 10.59
10.00	76.69	*1200	Lt/Wt 1250
11.00	77.40	1250	CaOI 1.04
12.00	77.19	*1200	L.P 25.54
1.00	77.69	*1200	
2.00	78.19	*1200	
3.00	77.44	*1200	
4.00	77.94	*1200	
5.00	77.68	1250	
6.00	77.40	1250	
7.00	77.19	1250	
8.00	77.43	*1200	
Average	77.62	1250	

Compressive Strength

3 Days	7 Days	28 Days
3535 (Disp) Slag	4506 (Disp) Slag	--
3650 (Disp) OPC	4738 (Disp) OPC	--

C.C.
 Director Project
 G.M (Project)
 G.M (Coord)
 D.G.M (Prod)

Manager (Q.C)

12/11